

## ::: EGALINE

### **Description:**

Is a calcium-sulfate-based self-levelling compound for levelling floors. It is used for smoothing and levelling uneven floor surfaces. Suitable for areas with low moisture exposure, both for heated and unheated substrates. Available in 25 kg packaging.

### **Application:**

Self-levelling compound according to DIN standard EN 13813, suitable for layer thicknesses from 2 mm to 30 mm. It cures quickly and is suitable for interior applications. Can be applied on cement screeds, calcium-sulfate screeds, concrete, dry-construction screeds, hollow floors, tile carrier elements, and well-adhering tiled floors.

### **Delivery Data**

Colour	grey
Viscosity	not applicable
Density	N/A
Shelf life	12 months in closed packaging
Consistency	powder

### **Technical data:**

Consumption	1.7 kg per m <sup>2</sup> per mm
Flexural strength	7 N/mm <sup>2</sup>
Compressive strength	20 N/mm <sup>2</sup>

### **Processing:**

Ensure a clean mixing bucket and fill it with the powder. Add the powder to the water in a 4:1 to 5:1 ratio. Mix for 3–5 minutes. Processing time: 30 minutes. Mix thoroughly and pour the mixture onto the dry and, if necessary, pre-treated substrate. Spread with a notched trowel until the desired layer thickness is achieved. Work in one layer and avoid high temperatures, direct sunlight, and draughts. Pay attention to the maximum moisture content present in the substrate.

### **Safety:**

Cleaning agent for tools: water. Is not classified as dangerous goods.

---

The information on this page concerns technical instructions and has been compiled to the best of our knowledge. However, it shall not constitute grounds for any liability on our part.